

## WOVEN GEOTEXTILE

Technical Data	Tex-w100	Tex-w200	Tex-w315
Formats	4.57 X 91.4 M	3.81 X 110 M	3.81 x 100 m / 4.57 x 91.4 m
Grab tensile	550 N	890 N	1402 N
Elongation		15%	
Puncture resistance	1425 N	3113 N	4005 N
Trapezoidal tear	200 N	330 N	503 N
UV Resistance (500 h)		70%	
AOS	0.600 mm	0.425 mm	0.425 mm
Permittivity	0.1 sec	0.05 sec	0.05 sec
Permeability	405 l/min/m <sup>2</sup>	240 l/min/m <sup>2</sup>	163 l/min/m <sup>2</sup>
General use	Control of unwanted weeds - Separation - Temporary cover	Separation – Stabilisation - Structural Reinforcement	Stabilisation - Structural Reinforcement -Technical Projects

The information contained herein is provided without charge or obligation on the part of Terraquavie. The presence of a product on this list does not constitute a commitment as long as its availability. All information on the products provided here must be validated from the technical sheet of said products. Terraquavie can in no way be held responsible for the quality, performance of the products and the consequences of improper installation or use. The product quality guarantee is limited to that provided by the manufacturer.