

DEWATERING BAGS

Technical data	PDS 6 oz	PDS 8 oz	PDS 10 oz
Tensile strength	712 N	911 N	1112 N
Elongation at break		50-105 %	
Trapezoid tear	267 N	356 N	444 N
CBR Puncture	1820 N	2380 N	3114 N
UV resistance (500h)		70%	
Apparente opening size (AOS)	0.212 mm	0.180 mm	0.150 mm
Flow rate	4480 l/min/m ²	4000 l/min/m ²	3251 l/min/m ²
Permittivity	1.5 Sec ⁻¹	1.4 Sec ⁻¹	1.2 Sec ⁻¹
Thread		Nylon 207 and 138	
Seams		Double lockstitch (J)	
Water inlet diameter		150 MM	
Standard dimensions	1.5m x 1.9m; 1.5m x 3.8m; 3.8m x 5m; 3.8m x 10m; 3.8m x 15m	2.2m x 3.5m; 4.5m x 5m; 4.5m x10m; 4.5m x 15m	2.2m x 3.5m; 4.5m x 5m; 4.5m x10m; 4.5m x 15m

The information herein is provided free of charge and without obligation on the part of Terraquavie. The person having this information in their possession assumes all responsibility for its use, including that of ensuring that this file represents the latest update by contacting Terraquavie. Terraquavie does not offer any guarantee regarding the use, installation and / or suitability of use of the products described in this document. Terraquavie cannot in any way be held responsible for product performance and the consequences of improper installation or use. Terraquavie must be informed of any product defect or non-conformity before installation. Terraquavie's liability will be limited to the replacement of the non-conforming or defective product.