

NONWOVEN GEOTEXTILES

Approved by MTQ (Québec Ministry of Transportation)

PROPRIETIES	TEX7605	TEX7609	TEX7612	TEX912	TEX918
Rolls format	3,81 x 150 m et 4.57 x 100 m				
Tensile strength	400 N	507 N	800 N	1000 N	1470 N
Elongation at break	50 %				
Puncture resistance CBR	1200 N	1570 N	2110 N	3300 N	4000 N
Tear strength	180 N	230 N	333 N	395 N	515 N
UV resistance (500 h)	70%			50%	
AOS	100-250	60-180	45-150	45-150	45-150
Permittivity	2.05 sec	1.34 sec	0.96 sec	0.67 sec	0.30 sec
Main function	Separation			Protection	
MTQ class before 2020	TYPE 4	TYPE 3	TYPE 6	TYPE 5	N.A.
MTQ class after 2020	F1	SI-F2	S2-P1	P2	P3

The information contained herein is provided at no cost or obligation on Terraquavie's part. The presence of a product on this list does not constitute a commitment as long as its availability. All information on the products provided here must be validated from the technical sheet of said products. Terraquavie can in no way be held responsible for the quality, performance of the products and the consequences of improper installation or use. The product quality guarantee is limited to that provided by the manufacturer.