

## HIGHT PERFORMANCE GEOTEXTILE

Technical Data	Tex-gf733	Tex-w4x6	Tex-hp270
Formats	3.65 X 91.5 m	4.6 X 91.5 m	4.5 x 91 m et 5.2 x 114 m
Grab tensile	1 647 X 1 113 N	2 670 X 3 115 N	38,5 KN/m
Elongation	15%	15%	N.D.
Puncture reistance	534 N	13 334 N	N.D.
Trapezoidal tear	445 X 267 N	801 X 1 224 N	N.D.
UV Resistance (500 h)	90%	80%	80%
AOS	0.179 mm	0.425 mm	0.600 mm
Permittivity	0.28 sec	0.26 sec	0.6 sec
Permeability	733 l/min/m <sup>2</sup>	815 l/min/m <sup>2</sup>	1 630 l/min/m <sup>2</sup>

The information contained herein is provided without charge or obligation on the part of Terraquavie. The presence of a product on this list does not constitute a commitment as long as its availability. All information on the products provided here must be validated from the technical sheet of said products. Terraquavie can in no way be held responsible for the quality, performance of the products and the consequences of improper installation or use. The product quality guarantee is limited to that provided by the manufacturer.